








Product name		Product group	Production location
Breslau (7-Schlitz)		K2	Kessel
A mix of Westerwald and Maas clay forms the basis for this extruded facing brick.			
Colour			
No description			
Format			
Moulding method		Wirecut	
NF: 240 x 115 x 71 mm		Between batches the average size and color may slightly differ.	
Essential Characteristics - EN771-1			
 EN 771-1 - 0620-CPR-21691		 EN 771 - 1855-CPR-24909	
2+		2+	
Dimensional tolerances	T1		
Range	R1		
Active Soluble Salts	S2		
Mean Compressive strength	>=60 N/mm ²	Tested to the bed face	
Normalized Compressive strength	>= 60 N/mm ²	Tested to the bed face	
Dimensional stability	NPD		
Bond Strength general	0,15 N/mm ²		
Bond Strength thin layer	0,30 N/mm ²		
Reaction to fire	A1	Category	
Water absorption	<= 5% m/md		
Water vapour permeability	50/100		
Net dry density	2100 kg/m ³ (D1)		
Gross dry density	1800 kg/m ³ (D1)		
Thermal conductivity Lambda 50/50	<=0,62 W/m.K		
Durability against freeze thaw	F2	EN 772-22	
Dangerous substances	NL-BSB	According to Annex ZA 3	
Other Characteristics			
Initial rate of water absorption - Non-coated Bricks	0 - 0,5 kg/m ² .min (IW1)	Value according EN771-1:2011 - 5.3.8	
Initial rate of water absorption - Coated bricks	NPD	Value according EN771-1:2011 - 5.3.8	
Freeze/thaw resistance - PTV 23-002	NPD	NBN 27-009	
Thermal conductivity Lambda 90/90	NPD		
Thermal conductivity Lambda Ui	NPD		
Thermal conductivity Lambda Ue	NPD		
<div></div>			
Storage & handling		Cutting	
<div><div>- Store packs on a clean surface and cover them</div><div>- Process from multiple packs at the same time</div><div>- Follow the Vandersanden processing guidelines</div></div>		Dry Cutting with power tools may generate dust. This dust may contain silica or quartz particulate which may constitute a hazard. Persons undertaking work of this nature are advised to wear dust masks (FFP3).	
<div><div>* All our Coated bricks are only coated on the facing sides. Coated products are specially labeled and recognisable with a "C" logo on the top left-hand side of the packaging. Always check if using coated or non-coated bricks. Match the mortar to the specified initial water absorption.</div></div>			