

| Product name | | | Production location | |
|--|--------|---|---------------------|--|
| Genua Liscio (With taps, without chamfered edge, without spacers) | A4-12G | | Kessel | |
| Format | | | | |
| Moulding method Wirecut | | | | |
| KF80: 202 x 100 x 80 mm | | Between batches the average size and color may slightly differ. | | |
| Essential Characteristics - EN1344 | | | | |
| CE NPD | | Uk Cf | S NPD | |
| Reaction to fire | | A1 | | |
| External fire performance | | NPD | | |
| Dangerous substances | | NL-BSB | | |
| Transverse breaking load | | T4 (>=80,>=64) | Category | |
| Unpolished slip/skid resistance USRV | | U3 (>=55) | Category | |
| Thermal conductivity | | NPD | | |
| Durability against freeze thaw | | FP100 | Category | |
| Sustainable slip/skid resistance (PSRV) | | U2 (>=45) | Category | |
| Other Characteristics - EN1344 & BRL 2360 | | | | |
| Paver quality 1 | | A4-12G | Category | |
| Paver quality 1 Tolerances | | $=$ 0,4 $\sqrt{\text{dimensions}}$ | | |
| Paver quality 1 Range | | R1 | Category | |
| Water absorption | | <= 5% m/md | | |
| Abrasion resistance | | A2+ (<=750mm³) | Category | |
| Acid resistance | | C (<=7%) | Category | |
| Other Characteristics - PTV 910 | | | | |
| Standardized Quality Classes - PTV 910 | | NPD | | |
| Water absorption - PTV 910 | | W2 (<=5%,<=6%) | | |
| | | | | |

| Storage & handling | Cutting |
|--|---|
| Stock pavers on a clean surface and cover them Blend from different pavers (pack) at the same time Do not clean fresh masonry with hydrochloric acid | Dry Cutting with power tools may generate dust. This dust may contain silica or quartz particulate which may constitute a hazard. Persons undertaking work of this nature are advised to wear dust masks (FFP3). |