

Duodinet in and			Duo duotion la sation	
Genua (With taps, without chamfered edge,		Production location		
	A4-12	2	Kessel	
without spacers)				
Format				
Moulding meth		od Wirecut		
DF80: 204 x 67 x 82 mm		Between batches the average size and color may slightly differ.		
Essential Characteristics - EN1344				
C E NPD		Uk Cf	NPD NPD	
Reaction to fire		A1		
External fire performance		NPD		
Dangerous substances		NL-BSB		
Transverse breaking load		T4 (>=80,>=64)	Category	
Unpolished slip/skid resistance USRV		U3 (>=55)	Category	
Thermal conductivity		NPD		
Durability against freeze thaw		FP100	Category	
Sustainable slip/skid resistance (PSRV)		U2 (>=45)	Category	
Other Characteristics - EN1344 & BRL 2360				
Paver quality 1		A4-12	Category	
Paver quality 1 Tolerances		<= 0,4 √dimensions		
Paver quality 1 Range		R1	Category	
Water absorption		<= 5% m/md		
Abrasion resistance		A2+ (<=750mm³)	Category	
Acid resistance		C (<=7%)	Category	
Other Characteristics - PTV 910				
Standardized Quality Classes - PTV 910		NPD		
Water absorption - PTV 910		W2 (<=5%,<=6%)		
Storage & handling		Cutting		
Stock pavers on a clean surface and cover them		Dry Cutting with power tools may generate dust. This dust may		
Blend from different pavers (pack) at the same time		contain silica or quartz particulate which may constitute a		
Bound to the control of the Control		hazard. Persons undertaking work of this nature are advised		

to wear dust masks (FFP3).

- Do not clean fresh masonry with hydrochloric acid