






Product name		Production location	
Aragon (Without Chamfered Edge, with spacers)	A4-12G	Spijk	
Format			
Moulding method		Mould	
DF80: 206 x 67 x 81 mm		Between batches the average size and color may slightly differ.	
Essential Characteristics - EN1344			
<div>CE</div> <div>NPD</div>		<div>UKCA</div> <div>NPD</div>	
Reaction to fire		Klasse A1	
External fire performance		NPD	
Dangerous substances		NL-BSB	
Transverse breaking load		T4 (>=80,>=64)	Category
Unpolished slip/skid resistance USRV		U3 (>=55)	Category
Thermal conductivity		NPD	
Durability against freeze thaw		FP100	Category
Sustainable slip/skid resistance (PSRV)		U2 (>=45)	Category
Other Characteristics - EN1344 & BRL 2360			
Paver quality 1		A4-12G	Category
Paver quality 1 Tolerances		<= 0,4 √dimensions	
Paver quality 1 Range		R1	Category
Water absorption		<= 5% m/md	
Abrasion resistance		A2+ (<=750mm³)	Category
Acid resistance		C (<=7%)	Category
Other Characteristics - PTV 910			
Standardized Quality Classes - PTV 910		B	
Water absorption - PTV 910		W2 (<=5%,<=6%)	
<div><div></div><div></div><div></div><div></div><div></div></div>			
Storage & handling		Cutting	
<div>- Stock pavers on a clean surface and cover them</div> <div>- Blend from different pavers (pack) at the same time</div> <div>- Do not clean fresh masonry with hydrochloric acid</div>		Dry Cutting with power tools may generate dust. This dust may contain silica or quartz particulate which may constitute a hazard. Persons undertaking work of this nature are advised to wear dust masks (FFP3).	