

Product name	Product group	Production location
Old Farmhouse	L1	Lanklaar

The raw materials are excavated in Weichsel loam layers, the local loam of Aeolian origin dating from the Ice Age. This löss mainly consists of a silt-like fraction, suited ideally for the manufacturing of hand form bricks. By using specific sand types for surface covering, the desired colour is achieved.

Colour

a shade of red, red brown and white to brown black with appearance of reclaimed brick					
Format					
Moulding method Hand form					
DF: 214 x 101 x 65 mm		Between batches the average size and color may slightly differ.			
Essential Characteristics - EN771-1					
C€	EN 771-1 - CPR-97884 NOBC 0063 (ex 0620)	(Uk Cf	S	EN 771 - 1855-CPR-24914
	2+				2+
Dimensional tolerances			T2		
	Range		R1		
Active Soluble Salts			S2		

Range	R1	
Active Soluble Salts	S2	
Mean Compressive strength	>= 20 N/mm²	Tested to the bed face
Normalized Compressive strength	>= 20 N/mm²	Tested to the bed face
Dimensional stability	NPD	
Bond Strength general	0,15 N/mm ²	
Bond Strength thin layer	0,30 N/mm ²	
Reaction to fire	A1	Category
Water absorption	<= 14% m/md	
Water vapour permeability	5/10	
Net dry density	1740 kg/m³ (D1)	
Gross dry density	1630 kg/m³ (D1)	
Thermal conductivity Lambda 50/50	<=0,60 W/m.K	
Durability against freeze thaw	F2	EN 772-22
Dangerous substances	NL-BSB	According to Annex ZA 3
		·

Other Characteristics						
Initial rate of water absorption - Non-coated Bricks	1,5 - 4.0 kg/m².min	Value according EN771-1:2011 - 5.3.8				
	(IW3)	Value according EN7/1-1:2011 - 5.3.8				
Initial rate of water absorption - Coated bricks	0,5 - 1,5 kg/m².min	Volue according FN771 1,2011 F 2.9				
	(IW2)	Value according EN771-1:2011 - 5.3.8				
Freeze/thaw resistance - PTV 23-002	NPD	NBN 27-009				
Thermal conductivity Lambda 90/90	0,65 W/m.K					
Thermal conductivity Lambda Ui	0,697 W/m.K					
Thermal conductivity Lambda Ue	1,376 W/m.K					











Storage & handling

- Store packs on a clean surface and cover them
- Process from multiple packs at the same time
- Follow the Vandersanden processing guidelines

CuttingDry Cutting with power tools may generate dust. This dust may

contain silica or quartz particulate which may constitute a hazard. Persons undertaking work of this nature are advised to wear dust masks (FFP3).

^{*} All our Coated bricks are only coated on the facing sides. Coated products are specially labeled and recognisable with a "C" logo on the top left-hand side of the packaging. Always check if using coated or non-coated bricks. Match the mortar to the specified initial water absorption.