




Product name		Production location	
Bamberg (With Chamfered Edge, without spacers)		NPD	Oberlausitz
Format			
Moulding method		Wirecut	
KF45: 200 x 100 x 45 mm		Between batches the average size and color may slightly differ.	
Essential Characteristics - EN1344			
<div>CE</div> <div>NPD</div>		<div>UK CA</div> <div>NPD</div>	
Reaction to fire		A1	
External fire performance		NPD	
Dangerous substances		NPD	
Transverse breaking load		T4 (>=80,>=64)	Category
Unpolished slip/skid resistance USRV		U3 (>=55)	Category
Thermal conductivity		NPD	
Durability against freeze thaw		FP100	Category
Sustainable slip/skid resistance (PSRV)		NPD	Category
Other Characteristics - EN1344 & BRL 2360			
Paver quality 1		NPD	Category
Paver quality 1 Tolerances		<= 0,4 $\sqrt{\text{dimensions}}$	
Paver quality 1 Range		R1	Category
Water absorption		<= 6% m/md	
Abrasion resistance		NPD	Category
Acid resistance		NPD	Category
Other Characteristics - PTV 910			
Standardized Quality Classes - PTV 910		NPD	
Water absorption - PTV 910		W2 (<=5%,<=6%)	
<div><div></div><div></div><div></div><div></div><div></div></div>			
Storage & handling		Cutting	
<div>- Stock pavers on a clean surface and cover them</div> <div>- Blend from different pavers (pack) at the same time</div> <div>- Do not clean fresh masonry with hydrochloric acid</div>		Dry Cutting with power tools may generate dust. This dust may contain silica or quartz particulate which may constitute a hazard. Persons undertaking work of this nature are advised to wear dust masks (FFP3).	