



| Product name | | Production location | |
|--|-----|--|----------|
| Görlitz (With Chamfered Edge, without spacers) | NPD | Oberlausitz | |
| Format | | | |
| Moulding method | | Wirecut | |
| KF45: 200 x 100 x 45 mm | | Between batches the average size and color may slightly differ. | |
| Essential Characteristics - EN1344 | | | |
| <div>CE</div> <div>NPD</div> | | <div>UK CA</div> <div>NPD</div> | |
| Reaction to fire | | A1 | |
| External fire performance | | NPD | |
| Dangerous substances | | NPD | |
| Transverse breaking load | | T4 (>=80,>=64) | Category |
| Unpolished slip/skid resistance USRV | | U3 (>=55) | Category |
| Thermal conductivity | | NPD | |
| Durability against freeze thaw | | FP100 | Category |
| Sustainable slip/skid resistance (PSRV) | | NPD | Category |
| Other Characteristics - EN1344 & BRL 2360 | | | |
| Paver quality 1 | | NPD | Category |
| Paver quality 1 Tolerances | | <= 0,4 $\sqrt{\text{dimensions}}$ | |
| Paver quality 1 Range | | R1 | Category |
| Water absorption | | <= 6% m/md | |
| Abrasion resistance | | NPD | Category |
| Acid resistance | | NPD | Category |
| Other Characteristics - PTV 910 | | | |
| Standardized Quality Classes - PTV 910 | | NPD | |
| Water absorption - PTV 910 | | W2 (<=5%,<=6%) | |
| <div><div></div><div></div><div></div><div></div><div></div></div> | | | |
| Storage & handling | | Cutting | |
| <div>- Stock pavers on a clean surface and cover them</div> <div>- Blend from different pavers (pack) at the same time</div> <div>- Do not clean fresh masonry with hydrochloric acid</div> | | Dry Cutting with power tools may generate dust. This dust may contain silica or quartz particulate which may constitute a hazard. Persons undertaking work of this nature are advised to wear dust masks (FFP3). | |