

VIIIIBEII				
Product name	Product	group Production location		
Tambora	B1	Façade Beek		
A mix of different kinds of clay - "Brunsummer" and "Maas" - forms the basis for this facing brick. By using specific sand types for				
surface covering, the desired colour is achieved.				
Colour				
Dark brown with black shades				
Format				
Moulding method Hand form				
DF: 216 x 100 x 66 mm Between batches the		average size and color may slightly differ.		
Essential Characteristics - EN771-1				
EN 771 - CPR-53104 - NOBC	, 111	K		
EN 771 - CPR-53104 - NOBC 0063 (ex 0620)	O UI	EN 771 - 1855-CPR-24910		
0003 (CA 0020)		-		
2+		2+		
Dimensional tolerances	T2			
Range	R1			
Active Soluble Salts	S2			
Mean Compressive strength	>= 15 N/mm²	Tested to the bed face		
Normalized Compressive strength	>= 15 N/mm²	Tested to the bed face		
Dimensional stability	NPD			
Bond Strength general	0,15 N/mm²			
Bond Strength thin layer	0,30 N/mm²			
Reaction to fire	A1	Category		
Water absorption	<= 12% m/md			
Water vapour permeability	50/100			
Net dry density	1850 kg/m³ (D1)			
Gross dry density	1700 kg/m³ (D1)			
Thermal conductivity Lambda 50/50	<=0,51 W/m.K			
Durability against freeze thaw	F2	EN 772-22		
Dangerous substances	NL-BSB	According to Annex ZA 3		
Other Characteristics				
Initial rate of water absorption - Non-coated Bricks	1,5 - 4.0 kg/m².min	Value according EN771 1:2011 E 2.9		
	(IW3)	Value according EN771-1:2011 - 5.3.8		
Initial rate of water absorption - Coated bricks	NPD	Value according EN771-1:2011 - 5.3.8		
France /these resistance DTI / 22 002	NDD	NDN 37 000		

Other Characteristics			
Initial rate of water absorption - Non-coated Bricks	1,5 - 4.0 kg/m².min	V I 50774 4 2044 5 2 0	
	(IW3)	Value according EN771-1:2011 - 5.3.8	
Initial rate of water absorption - Coated bricks	NPD	Value according EN771-1:2011 - 5.3.8	
Freeze/thaw resistance - PTV 23-002	NPD	NBN 27-009	
Thermal conductivity Lambda 90/90	NPD		
Thermal conductivity Lambda Ui	NPD		
Thermal conductivity Lambda Ue	NPD		











Storage & handling	Cutting
	(

- Store packs on a clean surface and cover them
- Process from multiple packs at the same time
- Follow the Vandersanden processing guidelines

Dry Cutting with power tools may generate dust. This dust may contain silica or quartz particulate which may constitute a hazard. Persons undertaking work of this nature are advised to wear dust masks (FFP3).

^{*} All our Coated bricks are only coated on the facing sides. Coated products are specially labeled and recognisable with a "C" logo on the top left-hand side of the packaging. Always check if using coated or non-coated bricks. Match the mortar to the specified initial water absorption.